

# Novel UV-transparent 2-component polyurethane resins for Chip-on-Board LED micro lenses

M. Gutke<sup>a</sup>, J. Bauer<sup>a</sup>, V. Stoycheva<sup>a</sup>, A. Kaltenbach<sup>b</sup>, M. Burkhardt<sup>b</sup>, M. Gruenefeld<sup>c</sup>, M. Gamp<sup>c</sup>, M. Edling<sup>a</sup>, P. Steglich<sup>a</sup>, F. Heinrich<sup>a</sup>, S. Steffen<sup>e</sup>, C. Gerhard<sup>d</sup>, M. Herzog<sup>a</sup>, C. Dreyer<sup>a,e</sup>, S. Schrader<sup>a</sup>

<sup>a</sup> Technical University of Applied Sciences Wildau, Hochschulring 1, 15745 Wildau, Germany

<sup>b</sup> resintec GmbH, Hellsternstr. 1, 04895 Falkenberg/Elster, Germany

<sup>c</sup> EPIGAP Optronic GmbH, Koepenicker Str. 325, Hs. 40, 12555 Berlin, Germany

<sup>d</sup> University of Applied Sciences and Arts, Von-Ossietzky-Straße 99, 37085 Göttingen, Germany

<sup>e</sup> Fraunhofer Institute for Applied Polymer Research IAP, PYCO, Kantstrasse 55, 14513 Teltow, Germany

## Abstract

An optical high-performance plastic based on polyurethane elastomer (PU) was developed, which combines excellent UV transparency with high thermal stability, good hardness, high surface tension and a long pot life. The material is well suitable for microlens applications for Chip-on-Board (CoB) LED technology.

## Goal

Lighting optics with micro lenses and LEDs must be manufactured in a particularly cost-effective and flexible manner. The major challenge is to achieve excellent transparency, high temperature stability, good mechanical strength and long-term stability of the polymers.



## PU material and component specification

Polyurethane resPUR	OT-3000	OT-T24000	OT
<b>A-component</b>	Polyester polyol		
Polyol OH contend [mg KOH/g]	> 130	> 50	> 130
<b>B-component</b>	P-MDI**	HDI*	HDI*

\*Aliphatic isocyanate hexamethylene diisocyanate oligomer (HDI)


\*\*Aromatic methylenediphenyl diisocyanate polymers (P-MDI)

## Packaging and lens forming




Fabrication results dome-type package of InGaNo-CoB-LED with resPUR-OT at different surface tension and corresponding light distributions at  $\lambda = 525$  nm.

## Thermal properties




Differential scanning calorimetry (DSC) measurements at temperatures from -150 to 500 °C. The points indicate the glass transition temperatures  $T_g$  and the degradation temperatures  $T_d$  of the PU. Secondary reactions of the isocyanates are shown in the range from 150 to 220 °C.





Thermogravimetry (TGA) curve of the polyurethane. Temperature program: Heat from 20 °C to 600 °C with heating rate of 10 °C/min, in nitrogen atmosphere with a purge rate of 10 mL/minute. Marked are the 5 % weight loss temperatures.


## Optical properties




Simulated (red) and experimental (black) transmission and reflection spectra of PU thin films, measured with the low resolution ( $\lambda = 200 - 890$  nm) and superimposed with high-resolution reflection ( $\lambda = 400 - 600$  nm) spectrometer. The thin film interferences are used to determine the film thickness.



Optical properties of PU, refractive index  $n$  and extinction coefficient  $k_s$  determined by reflection and transmission measurement and Tauc-Lorentz [1, 2] and Lorentz exciton [3 - 5] oscillator model fit of thin films and thick plane-parallel plates of PU. The relatively high  $k_s$  in the long wavelength region of resPUR-OT-T24000 is caused by the exciton absorption and scattering effect.



Transmittance of optical polymers [6] at a film of 3.174  $\mu\text{m}$  compared to resPUR-OT . thickness



Laser scattering properties:

- resPUR-OT-3000 material, shows fluorescence and has a scattering coefficient of  $k_s = 5.1 \times 10^{-6}$ ,
- resPUR-OT-T24000,  $k_s = 7.5 \times 10^{-6}$
- resPUR-OT,  $k_s = 3.9 \times 10^{-7}$

The scattering coefficient  $k_s$  was determined by using Lambert-Beer's law.

## Summary:

- This optimized material (resPUR-OT) has an excellent transparency, high thermal stability up to 344 °C and provides the possibility of a simple and cost-effective dispensing technique to ensure a stable encapsulation of LEDs with the possibility of lens formation [7, 8].
- The optical properties and the parameters of the band structure of PU can be changed in a wide range by the mixing ratio of the material components.
- The method presented here turns out to be a useful approach for the development of optical materials. The result confirms that highly transparent PU can be produced from aliphatic isocyanates and polyester polyol with optimized mixing ratios.

## References:

- [1] G. E. Jellison and F. A. Modine, *Parameterization of the optical functions of amorphous materials in the interband region*, Appl. Phys. Lett., 69 (3), 371-373 (1996).
- [2] Erratum, G. E. Jellison and F. A. Modine, Appl. Phys. Lett., 69(14), 2137 (1996).
- [3] M. Cardona, *Modulation Spectroscopy*, Suppl. vol. 11 of Solid State Physics, edited by F. Seitz, D. Turnbull, and H. Ehrenreich, Academic, New York (1969).
- [4] P. Lautenschlager, M. Garriga, S. Logothetidis and M. Cardona, *Interband critical points of GaAs and their temperature dependence*, Phys. Rev. B 35, 9174 (1987).
- [5] D.E. Aspnes: *Modulation spectroscopy/electric field effects on the dielectric function of semiconductors*, In Handbook of Semiconductors, Vol. 2, ed. by M. Balkanski (North-Holland, Amsterdam, 1980) pp. 109–154.
- [6] W. S. Beich, N. Turnera, *Polymer optics design, fabrication, and materials*, Proc. of SPIE Vol. 7788, 778805 (2010), edited by David H. Krevor, William S. Beich, GS Plastic Optics, 408 St. Paul Street, Rochester, NY 14605 (2010).
- [7] J. Bauer, M. Gutke, M. Edling, S. Schrader, and C. Gerhard, *Verfahren zur Herstellung asymmetrischer oder asphärischer Linsen sowie Leuchteinheit mit einer derart hergestellten Linse*, Patent EP19196944, filed on 09/12/2019.
- [8] M. Burghardt, A. Kaltenbach, D. Krüger, J. Bauer, M. Gutke, S. Schrader, *Polyurethan Giesharz mit hoher UV Transparenz und hoher Temperaturstabilität*, Patent DE 10 2019 133 078.5, filed on 12/04/2019.